

## DONGGUAN HYSEAL CO., LTD

## **TECHNICAL DATA**

TECHNICAL DATA		Chair Chair Cha	ne Oran Oran
Description	BOPP Hot Melt Tape		
Colour	Transparent Press Press Press Press Press Press		
Backing material	Bi-Axial Oriented Polypropylene Film		
Adhesive	Pressure Sensitive Synthetic Rubber (Hot Melt)		
Physical Properties	S Comi Charles Cha	Average Standard	ASTM Test Method
Film Thickness by Gauge (+/-4%)		23 um	D3652
Coating Weight per SQM (+/-6%)		16 gr/m²	D3652
180° Peeling Adhesion		8.0 N/inch	D3330
Holding Power on Steel		≥ 48 hours	D3654
Tensile Strength (MD)		55 N/inch	D3759
Elongation at Break		≥ 105%	D3759
Application Temperature (min.)		15 °C	N/A
Application Temperature (max.)		60 °C	One N/A
Storage Temperature (min.)		5 °C	N/A
Storage Temperature (max.)		50 °C	N/A

## IMPORTANT !!

The adhesive properties are susceptible to change depending on several parameters such as the composition and condition of the substrate impurities in or on the substrate temperature and humidity of the storage and environmental conditions during the application. Etc.

The above mentioned information is average values as the result of production samples and are not a guarantee of a final result.

Before using the product the customer should carry out its own tests in order to determine the product suitability for its specific application in real operative conditions and according to its own requirements.

For a better application, do not store more than 6 months and keep the product in original packaging at 25C+ and 65% humidity.

The product should be protected from extreme temperature, humidity and direct sun lights.



東莞市與盛膠粘製品有限公司

地址:廣東省東莞市高埗鎮實蓮民營工業園

郵件: info@hyseal.com 網址: www.hyseal.com 郵給: 5232



