

No. AJFS2001000043FF

Date: JAN.17, 2020

Page 1 of 12

CONCORD CONTROL SYSTEMS PVT.LTD.

G-36, UPSIDC INDS. ESTATE, CHINHUT, DEWA ROAD, LUCKNOW - 226 019, (U.P.) INDIA

The following sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion. results apply to the sample as received. <u>Sample Name</u>: SILICONE RUBBER COATED ARAMID FABRIC <u>SGS Ref No.</u>: GZIN2001000024SC <u>Manufacturer</u>: YEEDAH COMPOSITE MATERIAL CO., LTD <u>Product Specification</u>: 1.2mm <u>Style/Item No.</u>: /

Test Requested:

EN 45545-2:2013+A1:2015 Railway applications—Fire protection on railway vehicles Part 2: Requirements for fire behaviour of materials and components, and testing according to Table 5 — Material requirement sets (R1), (R7)

Test Results: -- See attached sheet --

Test Period:

Sample Receiving Date	:	JAN.02, 2020
Test Performing Date	:	JAN.02, 2020 TO JAN.15, 2020

Signed for and on behalf of SGS-CSTC Co., Ltd. Anji Branch

Allen Zou Lab Manager





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <u>http://www.sgs.com/en/Terms-and-Conditions.sys.</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions.sys.</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions.sys.</u> and, for electronic format documents, advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document to exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unaut/horized alteration, forger or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report rafer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(8e-75) 8307 1443, or email: CN.Doccheck@gss.com



No. AJFS2001000043FF

Date: JAN.17, 2020

Page 2 of 12

I. Description of Test specimens

Sample Description	Silicone rubber coated aramid fabric
Color	Pink
Thickness	About 1.3mm
Exposed (test) surface	One surface
	T02 ISO 5658-2: About 800mm×155mm
Size of specimens	T03.01 ISO 5660-1: About 100mm×100mm
	T10.01/T10.02/T10.03/T11.01: About 75mm×75mm

II. Summary of test results

Requirement set (used for)	Test method reference	Parameter Unit	Test results *
	T02 ISO 5658-2	<i>CFE</i> kW/m²	21.8
R1 (IN1A [,] IN1B [,] IN1D [,]	T03.01 ISO 5660-1: 50 kW/m ²	MARHE kW/m ²	65.3
IN1E; IN4; IN5; IN6A; IN7: IN8:	T10.01 EN ISO 5659-2: 50 kW/m²	<i>D</i> s(4) dimensionless	270.7
IN9B; IN11; IN12A; IN12B; IN14;F5)	T10.02 EN ISO 5659-2: 50 kW/m ²	VOF₄ min	782.3
	T11.01 EN ISO 5659-2: 50 kW/m ²	CIT _G dimensionless	0.090
	T02 ISO 5658-2	CFE kW/m²	21.8
R7 (IN6B; IN12C; EX1A; EX1C; EX3; EX4; EX5; EX6A; EX7; EX8; EL3C)	T03.01 ISO 5660-1: 50 kW/m2	MARHE kW/m²	65.3
	T10.04 EN ISO 5659-2: 50 kW/m2	Ds max dimensionless	299.8
	T11.01 EN ISO 5659-2: 50 kW/m2	CIT _G dimensionless	0.090

* For the test details, please see the appendix of this test report.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditins/Terms-and-Conditions/Terms-and-Conditions/



Date: JAN.17, 2020 Page 3 of 12

III. Conclusion

According to the test results, the submitted sample **meets** the requirements of R1 (detailed in Table 5 of EN 45545-2:2013+A1:2015) for **HL1** Hazard Level Classification.

No. AJFS2001000043FF

According to the test results, the submitted sample **meets** the requirements of R7 (detailed in Table 5 of EN 45545-2:2013+A1:2015) for **HL2** Hazard Level Classification.

Requirement Test method Parameter Requirement HL1 HL2 HL3 Definition set (used for) reference Unit T02 CFE 20 20 20 Minimum ISO 5658-2 kW/m² а R1 (IN1A; IN1B; T03.01 MARHE а IN1D; IN1E; ISO 5660-1: Maximum 90 60 kW/m² 50 kW/m² IN4; IN5; IN6A; T10.01 *D*s(4) IN7; IN8; EN ISO 5659-2: 300 Maximum 600 150 dimensionless IN9B; 50 kW/m² IN11; IN12A; T10.02 IN12B; VOF₄ EN ISO 5659-2: Maximum 1200 600 300 IN14: min 50 kW/m² F5) T11.01 CITG EN ISO 5659-2: Maximum 1.2 0.9 0.75 dimensionless 50 kW/m² T02 CFE 20 20 20 Minimum ISO 5658-2 kW/m² R7 (IN6B; IN12C; T03.01 MARHE а EX1A; ISO 5660-1: Maximum 90 60 kW/m² EX1C; EX3; 50 kW/m² EX4; EX5; T10.04 Ds max EX6A; EX7; EN ISO 5659-2: Maximum 600 300 -dimensionless EX8: 50 kW/m² EL3C) T11.01 **CIT**_G EN ISO 5659-2: Maximum 1.8 1.5 dimensionless 50 kW/m²

Test Criteria for EN 45545-2:2013+A1:2015 Table 5 Material requirement sets (R1), (R7)

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condita</u>



Test Report No. AJFS2001000043FF Date: JAN.17, 2020 Page 4 of 12

^a If flaming droplets/particles are reported according to 5.3.7 EN 45545-2:2013+A1:2015, during the test ISO 5658-2, or for the special case of materials which do not ignite in ISO 5658-2 and are additionally reported as unclassifiable, the following requirements shall be added:

Test to the requirements of EN ISO 11925-2 with 30s flame application.

The acceptance requirements are:

- --- flame spread < 150 mm within 60s;
- --- no burning droplets/particles.

Statements:

This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which were tested.

The specimen was supplied by the sponsor and SGS-CSTC ANJI Branch was not involved in any selection or sampling procedure.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-eDocument.aspx. Attention is drawn to the limitation of liability, indermification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document cannot be reproduced except in full, without prior written approval of the Company, any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fulleet axtent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are restained for 30 days only. Attention: To check the authenticity of testing / Inspection report & certificate, please contact us at telephone:(86-75) 8307 1443, or email: CN.Doccheck@asas.com



No. AJFS2001000043FF

Date: JAN.17, 2020

APPENDIX 1: T02 ISO 5658-2:2006 Lateral flame spread

1. Conditioning

T: 23±2°C, R.H: 50±5%, until the test sample was conditioned to constant mass.

2. Test results

Specimen No.:	,	1		1	2			3	
Mass(g)	22	9.3	Heat for Sustained	22	7.6	Heat for Sustained	23	1.3	Heat for Sustained
Time to Ignition: (min: sec)	0:	41	Burning (MJ/m ²)	0:	35	Burning (MJ/m ²)	0:	39	Burning (MJ/m ²)
Time to Travel	min	sec		min	sec		min	sec	()
50 mm	0	57	2.87	0	50	2.52	0	54	2.72
100 mm	1	03	3.05	1	11	3.44	0	59	2.86
150 mm	1	14	3.40	1	15	3.45	1	10	3.22
200 mm	1	22	3.48	1	25	3.60	1	18	3.31
250 mm	1	50	4.16	1	55	4.35	1	47	4.04
300 mm	2	14	4.15	2	22	4.40	2	20	4.34
350 mm	3	13	4.63	3	34	5.14	2	58	4.27
400 mm	-	-	-	-	-	-	-	-	-
450 mm	-	-	-	-	-	-	-	-	-
500 mm	-	-	-	-	-	-	-	-	-
550 mm	-	-	-	-	-	-	-	-	-
600 mm	-	-	-	-	-	-	-	-	-
650 mm	-	-	-	-	-	-	-	-	-
700 mm	-	-	-	-	-	-	-	-	-
750 mm	-	-	-	-	-	-	-	-	-
Duration of Test (min: sec)		16	:14		15:	00		17:	44
Final Travel (mm)		37	70		35	50		39	0
CFE (kW/m ²)		21	.8		24	.0		19	.5

Observations during test: None

Calculated from the data in above table for each specimen for each of the parameters

		A.v.a.			
PARAMETER	1	2	3	Avg	
Average Heat for Sustained Burning (Qsb) (MJ/m ²)	3.96	4.19	3.84	4.00	
Critical Heat Flux at Extinguishment (CFE) (kW/m ²)	21.8	24.0	19.5	21.8	

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condita</u>



Test Report No. AJFS2001000043FF Date: JAN.17, 2020 Page 6 of 12

<u>APPENDIX 2: T03.01 ISO 5660-1:2015 Reaction-to-fire tests — Heat release, smoke production and mass</u> loss rate — Part 1: Heat release rate (cone calorimeter method), Heat flux: 50kW/m²

1. Conditioning

T: $23 \pm 2^{\circ}$ C, R.H: $50 \pm 5^{\circ}$, until the test sample was conditioned to constant mass.

2. Test result

Test orientation	Horizontal			
The exposed surface area of the test specimen/ m ²	0.0088			
Irradiance / (kW/m ²)		Ę	50	
Specimen No.	1	2	3	Average
Initial mass / g	18.4	18.9	19.1	18.8
Mass at sustained flaming / g	17.3	18.0	18.2	17.8
Remained mass / g	9.8	10.0	10.3	10.0
Sample Mass Loss / g/m ²	950	980	980	970.0
Average Mass Loss Rate m/ (g·m ⁻² ·s ⁻¹)	1.0	1.3	1.4	1.2
Average rate of specimen mass loss per unit	2.0	21	22	21
area $m_{A,10-90}$ / (g·m ⁻² ·s ⁻¹)	2.0	2.1	<i>L</i> . <i>L</i>	2.1
Time to sustained flaming / s	62	54	54	56.7
Whether re-insert the spark igniter 1)	No	No	No	
Maximum heat release rate per unit area / (kW/m ²)	159.6	159.0	148.9	155.8
Average heat release rate per unit area for 180s after ignition / $(kW/m^2)^{2}$	75.4	72.3	73.6	73.8
Average heat release rate per unit area for 300s after ignition / (kW/m^2)	52.3	54.3	52.9	53.2
Total heat release / (MJ/m ²)	19.9	20.3	20.9	20.4
Average effective heat of combustion / (MJ/kg)	23.4	22.4	23.3	23.0
Total smoke production per unit area over the non- flaming phase /m ² m ⁻²	11.4	10.8	3.6	8.6
Total smoke production per unit area over the flaming phase / m ² m ⁻²	283.0	304.0	239.6	275.5
Test duration / s ³⁾	1200	1200	1200	1200
Maximum value of average rate of heat emission (MARHE) / KW/m ²	65.0	66.6	64.2	65.3
Additional observations 4)		-		
Special mounting procedures ⁵⁾		-		

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <u>http://www.sgs.com/en/Terms-and-Conditions</u>.asgx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions</u>/Terms-and-conditions/Terms-and-Conditions, Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereion reflects the Company's findings at the time of its infervention only and within the limits of advised that information contained hereion reflects the Company's findings at the time of its infervention only and within the limits of transaction from exercising all their rights and obligations under the transaction document. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be proseculed to the fullest stemt of the 3Me. Unless otherwise stated the results shown in this test report refor rough to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone;(8e-755) 8307 1443, or email: CN.Doccheck@gss.com



No. AJFS2001000043FF

Date: JAN.17, 2020 Page 7 of 12

Remark:

- 1) If the flame extinguishes in less than 60 s after turning off the spark, re-insert the spark igniter and turn on the spark within 5 s, do not remove the spark until the entire test is completed.
- 2) The 180 s mean heat release readings shall be compared for the three specimens. If any of these mean readings differ by more than 10 % from the arithmetic mean of the three readings, then a further set of three specimens shall be tested unless the mean value is less than 10 kW m⁻².
- 3) Collect all data until:
 - a. 32 min after the time to sustained flaming (the 32 min consist of a 30 min test period, and an additional 2 min post-test period to collect data that will be time-shifted). Data are processed to the time to sustained flaming plus 30 min.
 - $\hfill\square$ b. 30 min have elapsed and the specimen has not ignited;
 - \Box c. XO₂ returns to a value greater than the pre-test value minus 100 µl/l of oxygen concentration for 10 min. The end of test is the beginning of the 10 min period
 - □ d. The mass of the specimen is less than 0.1 g for 60 s. The end of test is the beginning of the 60 s period.
 - ☑ e. 20min(specified in EN 45545-2:2013+A1:2015 T03.02).
- 4) Observe and record physical changes to the sample such as melting, swelling, and cracking.
- 5) Special mounting procedures that were used:
 - □ a. Samples that intumesce or deform so that they contact the spark plug prior to ignition, or the underside of the cone heater after ignition, shall be tested with the separation of 60 mm between the base plate of the cone heater and the upper surface of the specimen.
 - □ b. Other dimensionally unstable products, for example products that warp or shrink during testing, shall be restrained against excessive movement. This shall be accomplished with 4 tie wires. A tie wire is then looped around the sample holder and retainer frame assembly, so that it is parallel to and approximately 20 mm away from one of the 4 sides of the assembly. The ends of the wire are twisted together such that the wire is pulled firmly against the retainer frame. Excess wire is trimmed from the twisted section before testing. The 3 remaining wires shall be fitted around the specimen holder and retainer frame assembly in a similar manner, parallel to the three remaining sides.
 - \Box c. Materials that distort so extensively that they cannot be held by 4 wires should be tested using the fine wire grid made of (0,8 ± 0,1) mm with wire spacing of (20 ± 2) mm.
 - □ d. Materials that intumesce in a fluid phase such that molten materials overflow the edge frame or seep between the edge frame and the specimen holder invalidate the test. Therefore, such materials should be tested without the edge frame and should be housed in 0,1 mm thick aluminum tray wrappings which extends 10mm above the top edge of the test specimen.
 - e. Materials, such as fibres, which need to be both physically restrained or compressed to be tested at installed densities should be tested in a wire cage structure made of (1,0 ± 0,1) mm steel wire with (9 ± 1) mm spacing which provides appropriate artificial boundaries to enable the materials to be tested
 If No special mounting procedures that were used
 - $\ensuremath{\boxdot}$ f. No special mounting procedures that were used
- 6) Heat release rate (per unit area), expressed in kilowatts per square metre curve of specimens is given in figure 1.
- 7) The orifice constant is <u>0.040</u>; the exhaust flow rate is 0.024 ± 0.002 m³/s.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.gsg.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Document at http://www.gsg.com/en/Terms-and-Conditions.aspx and, for electronic format documents, at http://www.gsg.com/en/Terms-and-Conditions.aspx and, for electronic format documents, at http://www.gsg.com/en/Terms-and-Conditions.aspx and, for electronic Document as http://www.gsg.com/en/Terms-and-Conditions/Terms-end-Condit



Test Report

Curves:

No. AJFS2001000043FF

Date: JAN.17, 2020

Page 8 of 12



Figure 1

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, aspx. Attention is drawn to the limitation of liability, indermification and jurisdiction issues defined therein. Any holder of this document is a dvised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document cannot be reproduced except in full, without prior written approval of the Company, any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are reflected for 30 days only. Attention:To check the authenticity of testing / Inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@ass.com



Test Report No. AJFS2001000043FF Date: JAN.17, 2020 Page 9 of 12

APPENDIX 3: T10.01&T10.02&T10.04 EN ISO 5659-2:2017 Plastics—Smoke generation — Part 2: Determination of optical density by a single- chamber test. Heat flux 50kW/m² without pilot flame, test duration is 10min.

1. Conditioning

T: 23 \pm 2 °C, R.H: 50 \pm 5%, until the test sample was conditioned to constant mass.

2. Test Results

Parameters	1	2	3	Avg
Mass (g)	10.7	10.5	10.6	10.6
D _{s (1.5)}	148.5	207.1	177.9	177.8
D _{s (4)}	272.6	260.8	278.6	270.7
Ds (10)	240.3	229.0	247.7	239.0
VOF₄ min	790.7	774.2	782.1	782.3
D _{s max}	301.9	299.6	297.9	299.8
T (D _{s max}) s	155	116	142	137.7

NOTE:

 $D_{s(n)}$ is the specific optical density at nth min;

VOF4 is the cumulative value of specific optical densities in the first 4 min of the test.

 $D_{s max}$ is the maximum optical density in the test chamber.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indermification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document cannot be reproduced except in full, without prior written approval of the Company, any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-75) 8307 1443, or email: CN.Doccheck@ssac.com



Test Report No. AJFS2001000043FF Date: JAN.17, 2020 Page 10 of 12

APPENDIX 4: T11.01&T11.02 EN 45545-2:2013+A1:2015, Annex C Gas analysis in the smoke chamber EN ISO 5659-2, using FTIR technique. Heat flux 50kW/m² without pilot flame, test duration is 10min.

1. Conditioning

T: 23±2°C and R.H 50±5%, until the test sample was conditioned to constant mass.

2. Test results

1) <u>4 min after the test start</u>

Gas	1	2	3	Avg
Carbon Dioxide (CO ₂)	8211.3	7949.0	8672.6	8277.6
Carbon Monoxide (CO)	190.0	199.2	239.0	209.4
Hydrogen Fluoride (HF)	ND	ND	ND	ND
Hydrogen Chloride (HCl)	ND	ND	ND	ND
Hydrogen Bromide (HBr)	ND	ND	ND	ND
Hydrogen Cyanide (HCN)	5.7	7.2	7.4	6.8
Nitrogen Oxides (NO _x)	13.3	12.9	14.0	13.4
Sulphur Dioxide (SO ₂)	8.7	9.7	10.2	9.6

2) <u>8 min after the test start</u>

Gas	1	2	3	Avg
Carbon Dioxide (CO ₂)	9711.9	9978.4	10588.5	10092.9
Carbon Monoxide (CO)	428.9	428.3	452.9	436.7
Hydrogen Fluoride (HF)	ND	ND	ND	ND
Hydrogen Chloride (HCl)	ND	ND	ND	ND
Hydrogen Bromide (HBr)	ND	ND	ND	ND
Hydrogen Cyanide (HCN)	13.1	13.6	15.7	14.1
Nitrogen Oxides (NO _x)	13.8	14.0	14.9	14.2
Sulphur Dioxide (SO ₂)	9.2	9.0	8.5	8.9

Where, ND indicates Non-detected.

Note: All values given are in mg/m³.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions, aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condition



No. AJFS2001000043FF

Date: JAN.17, 2020

Page 11 of 12

3) Calculation of CIT_G

Gas component	Reference concentration; mg/m ³
Carbon Dioxide (CO2)	72 000
Carbon Monoxide (CO)	1 380
Hydrogen Fluoride (HF)	25
Hydrogen Chloride (HCl)	75
Hydrogen Bromide (HBr)	99
Hydrogen Cyanide (HCN)	55
Nitrogen Oxides (NO _x)	38
Sulphur Dioxide (SO2)	262

$$CIT_G = 0.0805 \cdot \sum_{i=1}^{i=8} \frac{C_i}{C_i}$$

Where,

 CIT_G – Conventional Index of Toxicity;

 C_i – Concentration of the ith gas;

 C_i - Reference concentration of the ith gas.

PARAMETER	1	2	3	Avg
CIT _G (4 min)	0.059	0.061	0.067	0.062
CIT _G (8 min)	0.087	0.088	0.095	0.090

To be continued...





No. AJFS2001000043FF

Photo Appendix:



SGS authenticate the photo on original report only ***End of Report***



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overfeaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indermification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document cannot be reproduced except in full, without prior written approval of the Company, any unauthorized alteration, forger or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone;(86-75) 8307 1443, or email: CN.Doccheck/@sec.com