Add: No.26, eMobile Park, Lane 3938, Huqingping Rd. Qingpu, Shanghai, China TEL:+86-21-32513559 FAX:+86-21-32513556

TECHNICAL DATA SHEET

V 1.1

DEG ALUMINIUM PASTE ZT-360

ZT-360 is for Autoclaved Aerated Concrete (AAC) blocks and panels. It contain diethylene glycol (DEG) as a pasting substance, and recommended for use wherever high storage temperatures and long transportation routes require excellent storage stability.

Item				Specifica	tion	Unit		
Non-Volatile Content				>80	%			
Volatile content				<20		%		
Active Aluminium content				≥92		%		
D50 Value				33-35	j	um		
D10 Value				'10-20)	um		
D90 Value				50-55	um			
Sieve Residue (260mesh)				<5	%			
Gasing time				≤30		mins		
				Gasing Rate				
2	4	8	12	16	20	26	28	Unit
0	20	30	50	70	90	100	100	%