



上海鸿运源化工有限公司

SHANGHAI HYYCHEM CO., LTD.

Add: No.26, eMobile Park, Lane 3938, Huqingping Rd. Qingpu, Shanghai, China
 TEL:+86-21-32513559 FAX:+86-21-32513556

TECHNICAL DATA SHEET

V 1.1

DEG ALUMINIUM PASTE ZT-300

ZT-300 is for Autoclaved Aerated Concrete (AAC) blocks and panels. It contain diethylene glycol (DEG) as a pasting substance, and recommended for use wherever high storage temperatures and long transportation routes require excellent storage stability.

Item	Specification	Unit							
Non-Volatile Content	>80	%							
Volatile content	<20	%							
Active Aluminium content	≥92	%							
D50 Value	38-40	um							
D10 Value	10-25	um							
D90 Value	60-65	um							
Sieve Residue (200mesh)	<5	%							
Gasing time	≤30	mins							
Gasing Rate									
2	4	8	12	16	20	24	26	28	Unit
0	20	40	50	70	80	90	100	100	%

All statements, information and data presented herein are believed to be accurate and reliable but are not to be taken as a guarantee, express warranty or implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which seller assumes legal responsibility, and they are offered solely for your consideration, investigation and verification. Statements or suggestions concerning possible use of this product are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe on any patent.